



Aquaprime PVC Primer

PVC Primer & Adhesion Promotor

Features

- ▶ PVC Primer
- ▶ One Part
- ▶ Fast Drying
- ▶ Contains Etching Compounds

Product Description

Aquaprime PVC Primer is a one part polyurethane based, primer and adhesion promotor to be used on PVC, prior to the application of all **PASCO** solvent and water based mebranes and sealants.

Features & Benefits

- One part
- Fast drying, approximately 30-60 minutes
- Contains special etching compounds

Uses

- Primer and adhesion promotor for various Pasco coatings and membranes on to PVC.
- Aquaprime PVC Primer can also be used to bond waterbased membranes to polyurethane based membranes.

Suitable Surfaces

- PVC, PVC construction materials and Dincel

** Seek advice from Pasco for other like non porous surfcaes*

Important: Due to potential surface variations **Pasco** strongly recommend that a trial test is completed prior to application tests to ensure adequate adhesion and compatability.

Preparation

All surfaces must be clean, dry, sound and free from dust, oil, rust, plaster dust, cement droppings, protrusions, old sealant or any other contamination. Surfaces must be free from release and curing agents.

Application

- Apply using a brush or roller
- Apply in a single coat, at the rate of 5-10 sq.m. per litre depending on the actual substrate.
- Allow primer to completely dry prior to the application of water based membranes. Minimum curing time of 60minutes.
- Apply solvent based membrane or sealant as soon as the primer has dried with some residual tack. Minimum curing time of 30minutes.

Precautions

- Follow the instructions as per the Product Safety Data Sheet
- Wear gloves and safety goggles
- Use in well ventilated areas
- Avoid contact with skin as it may burn or irritate the skin
- Avoid contact with the eyes and contact may be painful and irritating. If in eyes, flush immediately with copious amounts of clean water holding eye lid open. Seek medical attention.

www.pasco.net.au



Aquaprime PVC Primer

PVC Primer & Adhesion Promotor

Coverage

- Approximately 5-10 sq.m. per litre per coat, dependent on actual substrate to be coated.

Refer to 'Application'.

Colours

- Clear

Curing

Drying and curing of the product is affected by type and porosity of the surface, temperature, humidity, ventilation and method of application.

Therefore timeframe is approximately 30 to 60 minutes.

Storage

Store in opened containers in cool, dry area away from heat and sources of ignition. Open containers may develop skinning. Keep away from water ingress as the product reacts and cures when contact with water occurs.

Health and Safety

Follow the instructions as per the Product Safety Data Sheet. Wear gloves and safety goggles. Use only in well ventilated areas.

Avoid contact with skin and eyes. If on skin, remove contaminated clothing and wash skin with soap and water. A moisturizing lotion may be soothing. Avoid contact with eyes as contact may be painful or irritating. If in eyes, immediately rinse with copious amounts of clean, cold water holding eye lid open for 15 minutes. Seek medical attention.

Ingestion is unlikely, but if ingested give lots of water to drink. Do NOT induce vomiting and seek urgent medical attention.

For full safety data refer to the Product Safety Data Sheet. Observe precautions as per label. Read prior to using the product.

Pasco Construction Solutions Pty Ltd offers its' products for sale, subject to its standard terms and conditions of sale, which are available upon request. All endeavors have been made to ensure the information provided in this technical data sheet is accurate and correct, however as the use of this material is beyond the supplier's control, liability is limited to replacement of material proven faulty. It is the responsibility of the purchaser to ensure that the product is suitable for the specific application and that it is applied in accordance with the supplier's recommendations.



241 Ingles Street
Port Melbourne, VIC 3207
Ph: (03) 9429 9111

4/14 Tennyson Road
Gladesville, NSW 2111
Ph: (02) 9817 4441